

P.S. SUBLI LT -EASYWEED™ SUBLIBLOCK

SPECIFICATIONS

Composition	Average Thickness	Q Carrier	♣ Certifications			
PU	110 microns	Adhesive polyester	REACH n° 1907/2006/EU OEKO-TEX ® * CONFIDENCE IN TEXTILES STANDARD 100 14CX00061 CENTROCOT 14CX00061 CENTROCOT			

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
textiles colored with	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
sublimation inks	45°	60 gf	30 cm/sec	15 seconds	135°C (275°F)	Medium (2,5/3,5 bar)	hot/cold

- → Cut the material mirrored
- → Peel off excess material
- \rightarrow Place the decoration on the garment
- → Apply following the recommended parameters
- → Remove the carrier hot or cold

PRODUCT HIGHLIGHTS

- → Low temperature transfer
- → Specific for sublimation dyed fabrics
- → Stops ink migration on sublimation polyester fabrics

 $oldsymbol{\mathcal{L}}$ NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ ⊳ Position
Up to 40°C, best inside- out	NO	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



